

鋼管の外径・内径・肉厚・1mあたりの重量

A呼称		6A	8A	10A	15A	20A	25A	32A	40A	50A	65A	80A	100A	125A	150A	200A	250A	300A
B呼称		1/8B	1/4B	3/8B	1/2B	3/4B	1B	1+1/4B	1+1/2B	2B	2+1/2B	3B	4B	5B	6B	8B	10B	12B
外径 (mm)		10.5	13.8	17.3	21.7	27.2	34.0	42.7	48.6	60.5	76.3	89.1	114.3	139.8	165.2	216.3	267.4	318.5
SGP	肉厚 (mm)	2.0	2.3	2.3	2.8	2.8	3.2	3.5	3.5	3.8	4.2	4.2	4.5	4.5	5.0	5.8	6.6	6.9
	内径 (mm)	6.5	9.2	12.7	16.1	21.6	27.6	35.7	41.6	52.9	67.9	80.7	105.3	130.8	155.2	204.7	254.2	304.7
	重量 (kg/m)	0.419	0.652	0.851	1.31	1.68	2.43	3.38	3.89	5.31	7.47	8.79	12.2	15.0	19.8	30.1	42.4	53.0
STPG370 Sch40	肉厚 (mm)	1.7	2.2	2.3	2.8	2.9	3.4	3.6	3.7	3.9	5.2	5.5	6.0	6.6	7.1	8.2	9.3	10.3
	内径 (mm)	7.1	9.4	12.7	16.1	21.4	27.2	35.5	41.2	52.7	65.9	78.1	102.3	126.6	151.0	199.9	248.8	297.9
	重量 (kg/m)	0.369	0.629	0.851	1.31	1.74	2.57	3.47	4.10	5.44	9.12	11.3	16.0	21.7	27.7	42.1	59.2	78.3
STPG370 Sch80	肉厚 (mm)	2.4	3.0	3.2	3.7	3.9	4.5	4.9	5.1	5.5	7.0	7.6	8.6	9.5	11.0	12.7	15.1	17.4
	内径 (mm)	5.7	7.8	10.9	14.3	19.4	25.0	32.9	38.4	49.5	62.3	73.9	97.1	120.8	143.2	190.9	237.2	283.7
	重量 (kg/m)	0.479	0.799	1.11	1.64	2.24	3.27	4.57	5.47	7.46	12.0	15.3	22.4	30.5	41.8	63.8	94.0	129
SUS-TP Sch10S	肉厚 (mm)	1.2	1.65	1.65	2.1	2.1	2.8	2.8	2.8	2.8	3.0	3.0	3.0	3.4	3.4	4.0	4.0	4.5
	内径 (mm)	8.1	10.5	14.0	17.5	23.0	28.4	37.1	43.0	54.9	70.3	83.1	108.3	133.0	158.4	208.3	259.4	309.5
304系	重量 (kg/m)	0.278	0.499	0.643	1.03	1.31	2.18	2.78	3.19	4.02	5.48	6.43	8.32	11.6	13.7	21.2	26.2	35.2
310・316系	重量 (kg/m)	0.280	0.503	0.647	1.03	1.32	2.19	2.80	3.21	4.05	5.51	6.48	8.37	11.6	13.8	21.3	26.4	35.4
SUS-TP Sch20S	肉厚 (mm)	1.5	2.0	2.0	2.5	2.5	3.0	3.0	3.0	3.5	3.5	4.0	4.0	5.0	5.0	6.5	6.5	6.5
	内径 (mm)	7.5	9.8	13.3	16.7	22.2	28.0	36.7	42.6	53.5	69.3	81.1	106.3	129.8	155.2	203.3	254.4	305.5
304系	重量 (kg/m)	0.336	0.588	0.762	1.20	1.54	2.32	2.97	3.41	4.97	6.35	8.48	11.0	16.8	20.0	34.0	42.2	50.5
310・316系	重量 (kg/m)	0.338	0.592	0.767	1.20	1.55	2.33	2.99	3.43	5.00	6.39	8.53	11.1	16.9	20.1	34.2	42.5	50.8
SUS-TP Sch40	肉厚 (mm)	1.7	2.2	2.3	2.8	2.9	3.4	3.6	3.7	3.9	5.2	5.5	6.0	6.6	7.1	8.2	9.3	10.3
	内径 (mm)	7.1	9.4	12.7	16.1	21.4	27.2	35.5	41.2	52.7	65.9	78.1	102.3	126.6	151.0	199.9	248.8	297.9
304系	重量 (kg/m)	0.373	0.636	0.859	1.32	1.76	2.59	3.51	4.14	5.50	9.21	11.5	16.2	21.9	28.0	42.5	59.8	79.1
310・316系	重量 (kg/m)	0.375	0.640	0.865	1.33	1.77	2.61	3.53	4.16	5.53	9.27	11.5	16.3	22.0	28.1	42.8	60.2	79.6
SUS-TP Sch80	肉厚 (mm)	2.4	3.0	3.2	3.7	3.9	4.5	4.9	5.1	5.5	7.0	7.6	8.6	9.5	11.0	12.7	15.1	17.4
	内径 (mm)	5.7	7.8	10.9	14.3	19.4	25.0	32.9	38.4	49.5	62.3	73.9	97.1	120.8	143.2	190.9	237.2	283.7
304系	重量 (kg/m)	0.484	0.807	1.12	1.66	2.26	3.31	4.61	5.53	7.54	12.1	15.4	22.6	30.8	42.3	64.4	94.9	131
310・316系	重量 (kg/m)	0.487	0.812	1.13	1.67	2.28	3.33	4.64	5.56	7.58	12.2	15.5	22.8	31.0	42.5	64.8	95.5	131

※SS材は7850kg/m³、SUS304系は7930kg/m³、SUS310・316系は7980kg/m³として重量を自動計算したものであり、規格表に記載の数値と異なる場合があります